CATALOGUE

CV ANUGRAH TERANG SEJAHTERA




Range of Alloy

ALLOY	AL CONTENTS	ALLOYING ELEMENTS
6063	98.9%	Si 0.4 ; Mg 0.7
6005	98.7%	Si 0.8 ; Mg 0.5
6005A	98.4%	Si 0.8 ; Mg 0.5 ; Mn 0.3
6060	98.9%	Si 0.4 ; Mg 0.5 ; Fe 0.2
6061	97.9%	Si 0.6 ; Mg 1.0 ; Cu 0.25 ; Cr 0.2
6101	98.9%	Si 0.5; Mg 0.6

Temper

T0 : Annealed
T4:Solution heattreatedand naturally aged to a substantially stable condition
T5 : Cooled from an elevated temperature shaping process and artificially aged
T6 : Solution heat treated and artificially aged


ROUND TUBE



NO SECTION	D mm	T mm	W Kg/M	P mm
10114	4.00	1.00	0.026	12.57
10501	6.00	0.70	0.032	18.85
10526	6.50	1.50	0.064	20.42
10522	7.00	0.70	0.038	21.99
10504	7.10	0.90	0.048	22.31
10503	7.50	0.80	0.046	23.56
10502	7.80	0.70	0.042	24.50
1000	8.00	0.75	0.046	25.13
1062	8.00	0.80	0.049	25.13
1050	8.00	1.00	0.060	25.13
1051	8.00	1.20	0.069	25.13
10511	8.00	1.50	0.083	25.13
1002A	8.50	0.70	0.046	26.70
1002	8.50	0.75	0.049	26.70
1001A	8.70	0.75	0.051	27.33
1063	8.70	0.80	0.054	27.33
1045B	9.00	0.70	0.049	28.27
1045	9.00	0.75	0.053	28.27
1045A	9.00	0.80	0.056	28.27
10041	9.40	0.80	0.059	29.53
1004A	9.53	0.80	0.059	29.94
1004	9.53	0.90	0.066	29.94
1077	9.53	1.00	0.073	29.94
1077 A	9.53	1.50	0.103	29.94
10574	9.53	1.50	0.103	29.94
1078	10.00	2.50	0.160	31.42


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROUND TUBE



NO SECTION	D mm	T mm	W Kg/M	P mm
1003	10.70	0.75	0.064	33.62
1061	10.70	0.80	0.068	33.62
1003A	10.70	1.50	0.117	33.62
1038	11.00	0.70	0.061	34.56
10051	11.00	1.00	0.085	34.56
1038 A	11.00	2.00	0.153	34.56
1005	11.50	0.80	0.073	36.13
1054	11.50	1.00	0.089	32.99
0508	11.50	1.70	0.142	36.13
10065	12.00	3.40	0.249	37.70
10064	12.00	4.40	0.285	37.70
10063	12.20	1.20	0.112	38.33
1007B	12.70	0.82	0.083	39.90
1007	12.70	0.90	0.090	39.90
1064	12.70	1.00	0.100	39.90
1006A	12.70	1.20	0.118	39.90
1075	13.00	0.70	0.073	40.85
10757	13.00	2.50	0.223	40.84
1056	14.00	0.80	0.090	43.98
1079	14.00	1.20	0.131	43.98
1042	14.06	0.70	0.080	44.17
1008	15.00	0.80	0.097	47.12
10592	15.80	1.50	0.183	49.64
1009	15.88	0.90	0.115	49.89
1010A	15.88	1.15	0.144	49.89
10095	15.88	1.90	0.226	49.89


ROUND TUBE



NO SECTION	D mm	T mm	W Kg/M	P mm
1010	16.00	1.00	0.128	50.27
1090	16.00	1.20	0.151	50.27
0513	16.00	1.70	0.207	50.27
1039	17.00	0.70	0.097	53.41
1055	17.00	0.80	0.110	53.41
1011B	17.50	3.00	0.370	54.98
0502	17.80	1.50	0.208	55.92
1012B	18.00	0.80	0.117	56.55
1092	18.00	1.50	0.211	56.55
10125	18.75	1.45	0.214	58.91
10681	19.00	1.20	0.182	59.69
1068	19.00	1.30	0.196	59.69
05019	19.00	1.90	0.277	59.69
10689	19.00	5.50	0.632	59.69
1012	19.05	0.90	0.139	59.85
1057	19.05	1.00	0.154	59.85
10594	19.05	1.20	0.182	59.85
1076	19.55	1.25	0.195	61.42
0501	19.05	1.50	0.224	59.85
0501 A	19.05	3.00	0.410	59.85
1043	20.00	0.70	0.115	62.83
1065	20.00	0.80	0.131	62.83
1013	20.00	1.50	0.236	62.83
10133	20.00	1.70	0.265	62.83
100	20.00	2.00	0.306	62.83
10134	20.00	2.50	0.372	62.83


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROUND TUBE



NO SECTION	D mm	T mm	W Kg/M	P mm
10132	20.00	3.00	0.434	62.83
1014	21.00	0.70	0.121	65.97
1014A	21.00	0.80	0.138	65.97
0509	21.00	1.70	0.279	65.97
0504	21.00	2.50	0.394	65.97
1015	22.00	0.75	0.136	69.12
1060	22.00	0.80	0.144	69.12
10731	22.00	1.10	0.196	69.12
10162	22.00	1.20	0.213	69.12
1016	22.00	1.50	0.262	69.12
1016 C	22.00	1.65	0.286	69.12
10163	22.00	1.80	0.310	69.12
1073	22.00	1.90	0.325	69.12
1016 A	22.00	2.00	0.341	69.12
1049	22.00	4.00	0.613	69.12
KMI 015	22.10	0.90	0.162	69.43
10606	22.10	3.55	0.561	69.43
1017 B	22.20	2.50	0.419	69.74
1017	22.23	0.90	0.163	69.84
1017 D	22.23	0.90	0.163	69.84
1066	22.23	1.00	0.181	69.84
10523	22.30	1.40	0.249	70.06
10156	22.50	0.70	0.130	70.69
10362	23.00	0.70	0.133	72.26
10364	23.00	0.70	0.133	72.26
1036	23.00	0.75	0.142	72.26


ROUND TUBE



NO SECTION	D mm	T mm	W Kg/M	P mm
1058	23.00	0.80	0.151	72.26
10361	23.40	0.70	0.135	73.51
10363	23.40	0.70	0.135	73.51
10585	23.50	1.20	0.228	73.83
10374	24.00	0.70	0.139	75.40
10373	24.00	0.75	0.148	75.40
10371	24.00	0.90	0.177	75.40
10372	24.50	0.70	0.142	76.97
1037	24.50	0.75	0.152	76.97
10375	24.75	1.45	0.288	77.75
1040	25.00	0.70	0.145	78.54
1082	25.00	0.90	0.185	78.54
1088	25.00	1.00	0.204	78.54
10882	25.00	1.10	0.224	78.54
1021C	25.00	1.20	0.243	78.54
0510	25.00	1.25	0.253	78.54
0521	25.00	1.30	0.262	78.54
0514	25.00	1.40	0.281	78.54
1041	25.00	1.50	0.300	78.54
1019	25.00	1.70	0.337	78.54
10191	25.00	1.80	0.356	78.54
1072	25.00	1.90	0.374	78.54
1020	25.00	2.00	0.392	78.54
1018	25.20	0.80	0.166	79.17
1021A	25.40	0.90	0.188	79.80
1021	25.40	1.00	0.208	79.80


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROUND TUBE



NO SECTION	D mm	T mm	W Kg/M	P mm
1021B	25.40	1.20	0.247	79.80
10524	25.40	1.40	0.286	79.80
1096	25.40	1.50	0.305	79.80
10525	25.40	3.18	0.602	79.80
1091	26.00	2.00	0.409	81.68
1023	28.00	2.90	0.620	87.96
0512	28.00	7.00	1.252	87.96
0520	28.40	1.50	0.344	89.22
0516	28.50	1.30	0.301	89.54
0534	30.00	1.00	0.247	94.25
0530	30.00	1.30	0.318	94.25
0531	30.00	1.70	0.410	94.25
0533	30.00	1.85	0.443	94.25
0532	30.00	2.00	0.477	94.25
1025	30.50	2.50	0.596	95.82
1034	31.00	9.25	1.713	97.39
10532	31.70	0.80	0.210	99.59
10271	31.70	0.90	0.236	99.59
1098	31.70	1.00	0.261	99.59
1052	31.75	1.20	0.312	99.75
1022	31.75	2.00	0.507	99.75
10224	31.75	2.40	0.600	99.75
10981	31.90	1.00	0.263	100.22
05032	32.00	1.20	0.315	100.53
05035	32.00	1.50	0.390	100.53
0503	32.00	4.00	0.954	100.53


ROUND TUBE



NO SECTION	D mm	T mm	W Kg/M	P mm
1027	33.00	0.95	0.259	103.67
10276	33.00	5.25	1.240	103.67
1074	34.00	1.50	0.415	106.81
10741	34.00	1.55	0.428	106.81
1024	34.00	3.75	0.966	106.81
1074 A	34.60	1.50	0.423	108.70
10246	34.80	3.65	0.968	109.33
1097	35.00	1.50	0.428	109.96
1053	35.00	2.00	0.562	109.96
10535 A	36.50	5.15	1.375	196.98
1059	37.50	3.75	1.078	117.81
10538	37.70	3.85	1.110	118.44
10537 A	37.80	1.55	0.478	118.75
1044	38.00	1.25	0.391	119.38
10537	38.00	1.50	0.466	119.38
0506	38.00	2.00	0.613	119.38
1099	38.10	1.15	0.362	119.69
10996	38.10	1.60	0.497	119.69
110 B	38.10	2.30	0.701	119.69
1047	38.50	4.05	1.188	120.95
10539	39.40	2.20	0.697	123.78
1067	40.00	2.50	0.798	125.66
1032	40.00	8.25	2.230	125.66
10896	41.00	2.00	2.656	257.61
1026	41.00	3.50	1.117	128.81
1087	41.00	3.60	1.146	128.81


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROUND TUBE




NO SECTION	D mm	T mm	W Kg/M	P mm
1094	41.10	4.60	1.429	129.12
1031	41.10	5.60	1.693	129.12
1071 A	42.00	1.80	0.616	131.95
1071	42.00	2.00	0.681	131.95
10711	42.40	1.85	0.639	133.20
02035	45.00	12.00	3.371	141.37
0505	46.00	3.50	1.266	144.51
1033	47.30	11.20	3.442	148.60
10337	48.40	2.70	1.051	152.05
0511	50.00	2.00	0.817	157.08
0507	50.00	4.00	1.567	157.08
1093	50.70	2.35	0.967	159.28
1070	50.70	4.00	1.590	159.28
1086	50.70	4.575	1.796	159.28
1048	50.70	6.15	2.333	159.28
1028	50.70	6.30	2.381	159.28
1029	50.70	12.60	4.087	159.28
1070 A	50.70	12.60	4.087	159.28
10541	50.80	1.20	0.507	159.59
1080	50.80	1.80	0.751	159.59
1080 A	50.84	1.92	0.800	159.72
10939	59.00	17.50	6.183	185.35
10557	60.33	1.80	0.897	189.53
10555	60.93	3.30	1.619	191.42
1035	61.00	6.00	2.810	191.64
1030	62.00	8.00	3.678	194.78

ROUND TUBE




NO SECTION	D mm	T mm	W Kg/M	P mm
10553	63.50	1.25	0.662	199.49
10305	64.01	3.30	1.707	201.09
10691	73.025	7.01	3.941	229.41
1069	75.50	6.00	3.550	237.19
10692	75.50	6.50	3.818	237.19
0517	76.20	0.90	0.577	239.39
0517 B	76.20	1.20	0.766	239.39
1083	76.20	1.50	0.954	239.39
0517 A	76.20	3.00	1.870	239.39
1089	83.00	1.20	0.836	260.75
1046	88.90	1.50	1.116	279.29
10853	91.20	7.50	5.344	286.51
1085	95.00	2.50	1.969	298.45
10851	98.40	4.20	3.368	309.13
10567	100.0	1.30	1.092	314.16
10859	114.30	6.02	5.549	359.08




NO SECTION	D mm	T mm	W Kg/M	OP mm
1331	23.01	0.90	0.123	75.41
1333	24.20	0.91	0.129	79.16

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROUND TUBE




NO SECTION	D mm	T mm	W Kg/M	OP mm
1321	19.00	0.80	0.108	61.39
1322	20.00	0.80	0.114	64.38
1323	21.05	0.80	0.126	67.17
1303	21.80	0.90	0.142	69.65
1304	25.00	0.85	0.150	80.22
1341	25.50	1.30	0.238	80.94
1342	28.30	1.30	0.268	89.86
1343	31.80	1.30	0.300	100.47



NO SECTION	D mm	T mm	W Kg/M	OP mm
1301	31.20	9.20	1.641	107.41
1306	33.10	9.55	1.822	112.03
1312	34.90	10.45	2.084	118.92
1302	39.90	7.45	1.954	138.31
1313	42.70	8.85	2.440	149.39
1310	43.90	8.45	2.436	149.63


SQUARE HOLLOWS



NO SECTION	A mm	T mm	R mm	W Kg/M	OP mm
1126	11.00	0.70	0.40	0.078	44.00
1101	11.50	0.80	0.40	0.092	46.00
1135	12.70	0.80	0.40	0.103	50.80
1119 A	12.70	0.90	0.40	0.115	50.80
1119	12.70	1.00	0.40	0.127	50.80
11364	15.00	1.40	0.40	0.206	60.00
1136	15.88	1.00	0.40	0.161	63.52
1161	16.00	0.70	0.40	0.116	64.00
1105	16.00	0.80	0.40	0.131	64.00
1112	17.00	0.70	0.40	0.124	68.00
1116	17.00	0.80	0.40	0.140	68.00
11171	18.00	0.70	0.40	0.131	72.00
1103	18.00	0.75	0.40	0.140	71.14
1117	18.00	0.80	0.40	0.149	72.00
11182	19.00	1.20	0.40	0.232	76.00
1118 A	19.05	0.90	0.40	0.177	76.20
1137	19.05	0.90	0.40	0.177	76.20
1118	19.05	1.00	0.40	0.196	76.20
1148	19.05	1.50	0.40	0.285	76.20
1111	19.20	0.80	0.40	0.160	76.80
1102	20.00	0.70	0.40	0.146	80.00
11622	20.00	1.20	0.50	0.244	79.14
11623	20.00	1.30	0.40	0.264	80.00
1162	20.00	1.40	0.40	0.282	104.16
1102 A	20.00	2.00	0.40	0.390	80.00
1123	20.00	2.20	0.40	0.424	79.48
1104A	20.50	0.70	0.40	0.150	82.00


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

SQUARE HOLLOWS



NO SECTION	A mm	T mm	R mm	W Kg/M	OP mm
1104	20.50	0.80	0.40	0.170	82.00
1110	21.60	0.80	0.40	0.180	86.40
1152	21.60	1.70	0.40	0.367	86.40
1113	23.00	0.70	0.40	0.169	92.00
1122	23.00	0.75	0.40	0.181	92.00
1127	23.00	0.80	0.40	0.193	92.00
1107	23.50	0.80	0.40	0.196	94.00
1106	24.00	0.80	0.40	0.201	96.00
1160	25.00	0.70	0.40	0.184	100.00
1114A	25.00	0.70	0.40	0.184	100.00
1114	25.00	0.80	0.40	0.210	100.00
1108	25.00	0.90	0.40	0.235	100.00
11082	25.00	1.20	0.40	0.310	100.00
11084	25.00	1.40	0.70	0.357	98.80
1128	25.00	2.00	2.50	0.484	95.71
1124	25.00	2.00	0.40	0.499	100.00
1138	25.40	0.90	0.40	0.239	101.60
1109	25.40	1.00	0.40	0.264	101.60
1109 B	25.40	1.20	0.40	0.315	101.60
1155	25.40	1.50	0.40	0.389	101.60
1153	25.40	1.70	0.40	0.437	101.60
1128 A	25.40	2.00	0.40	0.507	101.60
1139	25.40	2.00	0.40	0.507	101.60
11396	25.40	2.60	0.40	0.643	101.60
1140	25.40	2.80	0.40	0.686	101.60
1168	30.00	2.00	0.40	0.607	120.00
1149	31.75	1.10	0.40	0.365	127.00


SQUARE HOLLOWS



NO SECTION	A mm	T mm	R mm	W Kg/M	OP mm
1150	31.75	2.00	0.40	0.645	127.00
1141	38.10	1.00	0.40	0.402	152.40
11029	38.10	1.50	0.40	0.595	152.40
11708	40.00	0.80	0.40	0.340	160.00
11702	40.00	1.00	0.40	0.423	160.00
11705	40.00	1.20	0.40	0.505	160.00
11704	40.00	1.40	2.50	0.574	155.71
11706	40.00	1.60	0.40	0.666	160.00
11701	40.00	2.00	2.50	0.810	155.71
1167	40.00	3.30	0.40	1.313	160.00
11011	44.45	1.20	0.40	0.563	177.80
11663	50.00	1.20	2.50	0.624	195.71
1115	50.00	1.25	2.50	0.650	195.71
11662	50.00	1.40	0.70	0.736	198.80
11661	50.00	1.50	2.50	0.779	195.71
11151	50.00	1.50	0.40	0.789	200.00
1125	50.00	1.80	0.40	0.940	200.00
11258	50.00	1.80	2.00	0.931	196.57
11154	50.00	1.90	4.00	0.964	193.13
1121	50.00	2.00	2.50	1.026	195.71
1151	50.00	2.50	0.40	1.287	199.48
11153	50.00	3.00	0.40	1.528	200.00
1145	50.80	1.00	0.40	0.540	203.20
1146	50.80	2.00	0.40	1.058	203.20
1165	60.00	2.00	0.40	1.257	239.31
1154	60.00	4.00	0.40	2.428	240.00
1120	60.00	6.00	0.40	3.510	240.00


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

SQUARE HOLLOWS



NO SECTION	A mm	T mm	R mm	W Kg/M	OP mm
13700	12.70	1.00	2.50	0.118	46.51
13712	15.00	1.20	2.50	0.169	55.71
13715	15.00	1.50	2.50	0.207	55.71
13701	16.00	1.10	2.50	0.168	59.71
1374	19.00	1.00	2.50	0.186	71.71
13742	19.00	1.20	2.50	0.221	71.71
13743	19.05	1.50	2.50	0.273	71.91
13592	20.00	1.20	2.50	0.234	75.71
13593	20.00	1.30	2.50	0.252	75.71
13594	20.00	1.40	2.50	0.271	75.71
13598	20.00	1.80	2.50	0.342	75.71
13750	22.00	1.50	2.50	0.321	83.71
13581	25.00	1.10	2.50	0.275	95.71
13582	25.00	1.20	4.00	0.291	93.13
13512	25.00	1.20	1.60	0.304	97.25
13586	25.00	1.50	2.50	0.370	95.71
13585	25.00	1.6	3.00	0.389	94.85
13518	25.00	1.8	2.50	0.439	95.71
13519	25.00	2.00	3.00	0.480	94.85
1351	25.00	2.70	2.50	0.643	95.71
1354	25.40	1.50	2.50	0.379	97.31
13605	30.00	1.50	2.50	0.451	115.71
13604	30.00	1.90	2.50	0.565	115.71
13621	32.00	1.50	3.00	0.480	122.85
1362	35.00	1.70	4.00	0.589	133.13
13634	50.00	4.00	2.50	1.980	195.71
1363	60.00	2.00	3.00	1.239	234.85


RECTANGULAR HOLLOWS



NO SECTION	A mm	B mm	T mm	R mm	W Kg/M	OP mm
1288	17.00	9.50	0.70	0.40	0.095	53.00
1206	17.00	12.00	0.75	0.40	0.112	58.00
1214	17.00	12.00	0.80	0.40	0.119	97.00
1283	18.00	10.00	0.70	0.40	0.101	56.00
1231	19.50	9.50	0.70	0.40	0.099	58.00
12022	20.00	10.00	0.70	0.40	0.109	60.00
1202	20.00	12.00	0.90	0.40	0.147	64.00
12536	20.00	13.00	2.00	0.40	0.314	66.00
1284	21.00	10.50	0.70	0.40	0.114	63.00
1205	22.00	11.00	0.70	0.40	0.120	66.00
1213	22.00	11.00	0.80	0.40	0.136	66.00
1203 A	23.00	11.00	0.70	0.40	0.124	68.00
1212	23.00	12.00	0.70	0.40	0.127	70.00
1219	23.50	11.70	0.70	0.40	0.128	70.40
1203	23.50	12.40	0.80	0.40	0.149	71.80
1235	25.00	20.00	2.00	0.40	0.444	90.00
1201	25.40	12.70	0.90	0.40	0.177	76.20
1218	25.40	12.70	1.00	0.40	0.196	76.20
12029	30.00	15.00	1.50	0.40	0.341	90.00
1207	30.00	18.50	0.70	0.40	0.179	97.00
1215	30.00	18.50	0.80	0.40	0.203	97.00
12361	30.00	20.00	1.40	0.70	0.357	98.80
1202A	30.00	15.00	2.00	0.40	0.444	90.00
12362	30.00	20.00	1.20	0.40	0.310	100.00
12023	30.00	20.00	3.00	0.40	0.715	100.00
12151	31.00	19.00	1.80	0.40	0.453	100.00


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

RECTANGULAR HOLLOWS



NO SECTION	A mm	B mm	T mm	R mm	W Kg/M	OP mm
12152	32.00	18.00	2.20	2.00	0.535	96.57
12046	34.00	22.00	0.70	0.40	0.207	112.00
1204A	34.50	23.00	0.70	0.40	0.213	78.54
1204	34.50	23.00	0.80	0.40	0.242	115.00
1282	34.50	23.00	1.70	0.40	0.498	115.00
1290	35.00	23.00	0.70	0.40	0.215	116.00
1298	36.00	24.00	0.80	0.40	0.253	120.00
12081	38.10	25.40	0.80	0.40	0.268	127.00
1208	38.10	25.40	0.90	0.40	0.301	127.00
1217	38.10	25.40	1.00	0.40	0.333	127.00
12421	38.10	25.40	1.50	0.40	0.492	127.00
12858	40.00	20.00	0.80	0.40	0.253	120.00
12851	40.00	20.00	1.00	0.40	0.314	120.00
12857	40.00	20.00	1.20	0.40	0.375	120.00
1285	40.00	20.00	1.50	0.40	0.463	119.14
1285 A	40.00	20.00	2.00	0.40	0.607	120.00
1286	45.00	22.50	0.70	0.40	0.251	135.00
1297	45.00	22.50	1.50	0.40	0.524	135.00
1294	46.00	23.00	0.70	0.40	0.256	138.00
1221	48.00	23.00	0.70	0.40	0.264	142.00
12855	50.00	20.00	1.50	1.50	0.539	137.43
12854	50.00	20.00	1.50	2.50	0.532	135.71
1221 A	50.00	25.00	2.00	0.40	0.770	150.00
12853	50.00	20.00	3.00	0.40	1.041	140.00
12601	50.00	30.00	1.35	0.40	0.566	160.00
12603	50.00	30.00	3.10	2.00	1.231	156.57


RECTANGULAR HOLLOWS



NO SECTION	A mm	B mm	T mm	R mm	W Kg/M	OP mm
12604	50.00	40.00	2.50	0.40	1.152	179.48
1211 A	50.60	25.40	3.00	0.40	1.141	152.40
12092	50.80	25.40	0.80	0.40	0.323	152.40
12091	50.80	25.40	0.90	0.40	0.363	152.40
1209	50.80	25.40	1.00	0.40	0.402	152.40
1211	50.80	25.40	1.40	0.40	0.557	152.40
12006	50.80	38.10	2.00	0.40	0.920	177.80
1260 A	50.80	38.50	4.00	0.40	1.763	178.60
12965	60.00	15.00	1.50	0.40	0.585	150.00
12027	70.00	30.00	1.20	0.40	0.635	200.00
12161	76.20	25.40	0.85	0.40	0.460	203.20
1216	76.20	25.40	1.00	0.40	0.540	203.20
1210	76.20	25.40	1.20	0.40	0.645	203.20
12643	76.20	44.45	3.00	0.40	1.864	241.30
12608	80.00	30.00	2.00	0.40	1.149	220.00
12993	95.60	20.60	1.20	0.40	0.740	232.40
12201	100.00	10.00	1.70	0.40	0.982	220.00
12994	100.00	25.00	1.20	0.40	0.797	250.00
12995	100.00	38.00	2.30	0.40	1.663	276.00
12522	100.00	40.00	1.70	1.50	1.253	277.42
12521	100.00	50.00	2.00	1.50	1.577	297.43
1287	101.60	25.40	1.00	0.40	0.678	254.00
1220	101.60	25.40	1.10	0.40	0.744	254.00
12011	101.60	25.40	1.40	0.40	0.942	254.00
1238 A	101.60	50.80	3.00	0.40	2.380	304.80
12691	101.60	44.45	1.30	0.40	1.011	292.10


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

RECTANGULAR HOLLOWS



NO SECTION	A mm	B mm	T mm	R mm	W Kg/M	OP mm
12898	150.00	40.00	1.50	0.40	1.520	380.00
12897	150.00	100.00	2.50	0.40	3.320	500.00
1353	25.00	12.00	1.20	3.50	0.206	67.99
13538	25.00	12.00	1.80	3.50	0.304	67.99
1352	25.00	15.00	2.70	2.50	0.497	75.71
1369	25.00	20.00	1.40	2.50	0.308	85.71
13675	30.00	15.00	1.50	2.00	0.333	86.57
13674	30.00	20.00	1.40	1.80	0.351	96.91
13691	30.15	26.15	1.00	0.70	0.293	111.40
13651	35.00	10.00	1.20	2.00	0.269	86.57
13693	38.00	16.00	2.50	2.00	0.655	104.57
13640	38.00	25.40	1.60	2.50	0.509	122.51
13641	38.10	25.40	1.50	2.50	0.480	122.71
13571	40.00	15.00	1.20	1.00	0.340	108.28
13572	40.00	20.00	1.20	2.50	0.364	115.71
1357	40.00	20.00	1.45	2.50	0.437	115.71
13574	40.00	25.00	1.80	2.50	0.586	125.71
13575	40.00	30.00	2.00	2.00	0.715	136.57
13692	44.01	13.00	2.50	2.00	0.695	110.59
13694	48.00	16.00	2.50	2.00	0.790	124.57
13643	50.00	25.00	1.10	2.50	0.424	145.71
13645	50.00	25.00	1.50	1.50	0.580	147.43
13648	50.00	25.00	1.80	2.00	0.687	146.57
13642	50.80	25.40	1.50	2.50	0.583	148.11
13695	57.00	16.00	2.50	2.00	0.912	142.57
13578	80.00	40.00	2.30	2.00	1.429	236.57


ROUND BARS



NO SECTION	D mm	W Kg/M	P mm
1428 A	2.00	0.009	6.28
1428	3.00	0.019	9.42
1420	4.00	0.034	13.00
1430	4.10	0.036	12.88
1427	4.76	0.048	14.95
1401A	5.00	0.053	15.71
1434	6.00	0.077	18.85
1401	6.35	0.086	19.95
1435	6.80	0.098	21.36
1440	7.80	0.129	24.50
1403	8.00	0.136	25.13
1402	9.00	0.172	28.27
1404	9.50	0.193	29.85
1405	10.00	0.213	31.42
1405 A	10.70	0.244	33.62
1439	12.00	0.307	37.70
1406	12.70	0.343	39.90
1406A	14.20	0.429	44.61
1407	15.88	0.537	49.89
1433	16.00	0.545	50.27
1408	16.50	0.579	51.84
1409	19.05	0.772	59.85
1410 A	20.00	0.851	62.83
1410	20.50	0.894	64.40
14106	21.00	0.939	65.97


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROUND BARS



NO SECTION	D mm	W Kg/M	P mm
1411	22.20	1.049	69.74
1411B	22.70	1.097	71.31
1411A	23.80	1.206	74.77
14121	25.00	1.330	78.54
1412	25.40	1.373	79.80
1413	26.50	1.495	83.25
1418	28.00	1.669	87.96
1414	29.50	1.852	92.68
1414A	30.50	1.980	95.82
1415	31.75	2.146	99.75
1416	38.10	3.090	119.69
1417	39.00	3.237	122.52
1444	44.45	4.205	139.64
1419	50.80	5.493	159.59
1419 A	51.00	5.536	160.22
1421	57.15	6.952	179.54
1422	63.50	8.582	199.49
1423	69.85	10.385	219.44
1424	76.20	12.359	239.39
1425	82.55	14.504	259.34
1426	88.90	16.821	279.29
1442	92.50	18.211	290.60
1441	94.50	19.007	296.88
14291	101.60	21.971	319.19
1431	101.60	21.971	319.19


SQUARE BARS



NO SECTION	A mm	AREA mm	W Kg/M	P mm
1502	6.35	40.32	0.109	25.40
1503	9.53	90.82	0.246	38.12
1505	10.00	100.00	0.271	40.00
1504	12.70	161.29	0.437	50.80
1510	16.00	256.00	0.694	64.00
1524	19.05	362.77	0.983	75.51
1513	25.00	624.86	1.693	99.31
1526	25.40	645.16	1.748	101.60
1520	31.75	1007.20	2.730	125.28
1525	32.00	1024.00	2.775	128.00
1521	38.10	1451.61	3.934	152.40
1516	40.00	1599.86	4.336	159.31
1522	44.45	1975.80	5.354	177.80
1517	45.00	2024.14	5.485	178.28
1518	50.00	2500.00	6.775	200.00
1523	51.00	2601.00	7.049	204.00
1519	75.00	5625.00	15.24	300.00


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

FLAT BARS



NO SECTION	A mm	T mm	W Kg/M	OP mm
1606	10.70	1.00	0.029	23.40
1617	12.00	1.80	0.059	21.60
1600	12.70	0.80	0.028	27.00
1601	12.70	0.90	0.031	27.20
1619 A	12.70	0.90	0.031	27.20
1619	12.70	1.00	0.034	27.40
1717	13.80	8.60	0.321	44.11
1716	18.00	6.00	0.290	46.28
1647	19.00	6.00	0.309	50.00
1613	19.05	1.00	0.052	40.10
1629	19.05	1.00	0.052	40.10
16012	19.05	2.00	0.103	42.10
1602	20.00	2.00	0.108	44.00
1603	20.00	3.00	0.163	46.00
1615	20.00	3.60	0.195	47.20
16151	20.00	5.00	0.271	50.00
1611	23.50	0.80	0.051	48.60
1641	24.00	1.00	0.065	50.00
1642	24.00	2.90	0.189	53.80
1604	24.00	5.00	0.325	58.00
1621	25.00	2.50	0.169	55.00
1610	25.00	3.00	0.203	56.00
1637	25.00	5.00	0.339	60.00
16016 A	25.00	5.00	0.338	59.14
1618	25.40	0.90	0.062	22.83
1622	25.40	1.00	0.069	52.80
16311	25.40	7.00	0.482	64.80


FLAT BARS



NO SECTION	A mm	T mm	W Kg/M	OP mm
16319	25.40	9.53	0.656	69.86
16312	25.40	12.70	0.874	76.20
1643	30.00	1.00	0.081	62.00
1625	30.00	2.00	0.163	64.00
1614	31.75	0.90	0.086	65.50
16020	31.75	6.00	0.516	75.50
1640	32.00	3.00	0.260	70.00
16401	32.00	5.00	0.434	74.00
1644	35.00	1.00	0.095	72.00
1605	38.00	2.00	0.206	80.00
1626	38.00	2.50	0.257	95.00
1628	38.00	2.60	0.268	81.20
1627	38.10	3.20	0.330	81.74
1639	38.10	6.00	0.620	87.68
16056	38.10	9.53	0.984	95.26
16331	38.10	12.70	1.311	101.60
1737	38.10	31.75	3.278	139.70
16402	40.00	3.00	0.325	86.00
16403	40.00	5.00	0.542	90.00
16341	44.45	8.00	0.964	104.90
16342	44.45	25.40	3.060	139.70
16351	50.00	1.00	0.136	102.00
1636 A	50.80	3.00	0.413	107.60
1630 A	50.80	4.70	0.646	110.14
16361	50.80	8.00	1.100	117.60
16362	50.80	15.88	2.186	133.36
16316	50.80	25.40	3.497	152.40


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

FLAT BARS



NO SECTION	A mm	T mm	W Kg/M	OP mm
16363	50.80	38.10	5.245	177.80
1624	51.20	2.90	0.402	108.20
1623	59.80	1.90	0.308	123.40
16462	60.00	6.00	0.976	132.00
1607	60.00	10.00	1.626	140.00
16064	63.50	6.35	1.093	139.70
16198	63.50	12.70	2.185	152.40
16080	63.50	15.88	2.733	158.76
16298	63.50	19.05	3.278	165.10
16381	70.00	1.00	0.190	142.00
16088	76.00	10.50	2.163	173.00
1638	76.20	9.53	1.968	170.94
16086	76.20	15.88	3.278	184.15
16317	76.20	25.40	5.245	203.20
16082	76.20	31.75	6.556	203.20
16299	88.90	19.05	4.589	215.90
16083	101.60	9.53	2.624	222.26
16084	101.60	15.875	4.379	234.95
16085	101.60	25.40	6.994	254.00
16482	110.00	1.75	0.522	223.50
16485	110.00	6.00	1.789	232.00
1608	110.00	10.00	2.981	240.00
16486	120.00	5.00	1.626	250.00
1609	130.00	12.00	4.227	283.14
16079	160.20	5.60	2.431	331.60
1616	180.00	8.50	4.146	376.14
1616 B	180.00	20.00	9.755	398.71


EQUAL ANGLES



NO SECTION	A mm	T mm	W Kg/M	P mm
1800	8.00	0.75	0.031	32.00
1805	8.00	0.80	0.033	32.00
1802	12.00	0.75	0.047	48.00
18070	12.60	0.70	0.046	50.40
1801	12.70	0.80	0.053	50.37
1804	15.00	0.75	0.059	60.00
1807	15.00	0.80	0.063	60.00
18046	15.00	2.00	0.152	60.00
1803	17.00	0.75	0.068	68.00
1806	17.00	0.80	0.072	68.00
1886	20.00	2.00	0.206	80.00
1808	24.00	0.75	0.096	96.00
1873	25.00	3.00	0.382	99.36
1884	25.40	1.27	0.170	101.60
1809	28.00	0.75	0.112	112.00
1867	38.10	2.00	0.402	152.40
18019	38.10	5.80	1.107	152.40
18536	46.00	4.00	0.954	184.00
18543	50.00	4.00	1.041	200.00
18681	50.80	2.21	0.595	203.20
18561	50.80	8.00	2.029	203.20
1820	60.00	6.00	1.854	684.00
18201	63.50	6.00	1.967	254.00


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

UNEQUAL ANGLES




NO SECTION	A mm	B mm	T mm	W Kg/M	P mm
18471	13.00	8.00	1.20	0.064	42.00
18353	14.00	12.00	1.20	0.081	52.00
18354	15.00	12.00	1.40	0.097	54.00
18331	16.00	8.00	1.50	0.092	48.00
1833	16.00	12.00	1.50	0.108	56.00
18346	18.00	15.00	1.80	0.152	66.00
18367	20.00	12.00	1.20	0.100	64.00
18366	20.00	12.00	1.50	0.124	64.00
1836	22.00	8.00	1.80	0.124	110.00
18361	22.00	10.00	1.20	0.100	64.00
1831	22.00	14.00	1.80	0.166	70.93
18391	25.00	11.80	1.40	0.134	73.60
18358	26.50	12.70	1.20	0.124	78.40
18356	26.50	12.70	1.40	0.143	78.40
18359	26.50	12.70	1.50	0.153	78.40
18351	27.00	14.00	1.40	0.150	82.00
18352	27.00	13.00	1.55	0.162	80.00
1832	27.00	14.00	1.65	0.176	82.00
18357	30.00	18.00	2.00	0.249	96.00
1837	38.10	19.05	1.50	0.226	114.30
18425	50.00	25.00	1.60	0.318	150.00
18355	50.00	25.00	4.40	0.842	150.00
18433	95.00	35.00	2.00	0.694	260.00
18329	152.40	76.20	6.00	3.619	457.20

EQUAL ANGLES



NO SECTION	A mm	T mm	W Kg/M	P mm
1824	12.00	0.80	0.050	48.83
1823	12.20	0.80	0.053	50.17
1822	12.50	0.80	0.051	49.92
1821	12.70	0.80	0.053	50.93
1825	17.00	0.80	0.071	68.83


DECORATIVE ANGLES



NO SECTION	A mm	B mm	T mm	W Kg/M	P mm
1981	19.05	12.70	0.90	0.071	62.91
1979	22.50	13.50	1.70	0.157	72.99
1974	24.00	13.00	1.50	0.140	75.63
1982	25.40	12.70	0.90	0.086	75.61
1975	27.00	14.00	1.80	0.189	83.24


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

U–CHANNELS



NO SECTION	A mm	T mm	W Kg/M	P mm
1901	9.00	0.75	0.052	52.50
1905	9.00	0.80	0.055	52.50
1909	9.58	1.00	0.072	55.48
1902	12.00	0.75	0.070	70.40
1906	12.00	0.80	0.074	70.40
1910	12.70	0.90	0.088	74.40
1903	15.00	0.75	0.088	88.50
1907	15.00	0.80	0.094	88.50
1911	15.88	0.90	0.112	93.48
1912	15.88	2.40	0.279	90.48
1904	17.00	0.75	0.101	100.50
1908	17.00	0.80	0.107	100.50
1913	19.05	0.80	0.120	112.70
19142	19.05	2.00	0.288	110.30
1914	19.05	2.40	0.340	109.50
1918	20.00	0.90	0.142	118.20
19155	25.00	3.00	0.561	144.00
1915	25.40	1.00	0.201	150.40
19162	25.40	2.00	0.391	148.40
19165	25.40	2.50	0.482	147.40
1916	25.40	2.80	0.536	146.80


UU–CHANNELS



NO SECTION	A mm	B mm	T mm	W Kg/M	P mm
1954	6.50	11.50	0.70	0.053	57.60
1951	6.60	12.30	0.80	0.064	60.80
1952	7.00	12.50	0.80	0.066	64.40
1955	12.50	7.00	0.90	0.060	51.20
19050A	25.00	12.50	0.80	0.105	98.40
19069A	25.40	12.70	1.00	0.132	99.60
19069	25.40	19.05	1.00	0.167	125.00
19051	25.40	38.10	2.40	0.630	198.48
19052	25.40	50.80	2.80	0.920	248.40
19053	38.10	12.70	0.80	0.134	125.40
19063	38.10	25.40	2.80	0.632	172.20
19054	44.45	12.70	1.00	0.184	137.70
1971	48.00	12.00	0.80	0.153	142.40
19083	50.00	25.00	2.20	0.570	195.60
1970	50.80	12.50	0.90	0.180	149.80
19055	50.80	12.70	0.80	0.162	150.80
19080	50.80	12.70	1.05	0.211	150.30
19056	50.80	25.40	1.05	0.283	201.10
19057	50.80	25.40	2.80	0.728	197.60
19731	61.00	8.50	1.20	0.245	152.23
1973	75.00	38.00	2.90	1.141	296.20


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

UU–CHANNELS




NO SECTION	A mm	B mm	T mm	W Kg/M	P mm
19096	75.00	50.00	3.00	1.374	344.00
19098	76.20	19.00	1.00	0.304	226.40
19095	76.20	19.05	1.20	0.364	226.20
19060	76.20	38.10	3.00	1.190	298.80
19097	100.00	19.00	0.90	0.332	274.20
19062	101.60	50.80	2.80	1.499	400.80

DECORATIVE CHANNELS




NO SECTION	A mm	T mm	W Kg/M	P mm
1926	9.00	0.80	0.052	52.65
1929	12.50	0.80	0.075	74.16
1927	15.00	0.70	0.080	88.85
1928	17.00	0.70	0.091	100.88

TRANSPORT




2004A

W = 0.390 Kg/M
P = 210.03 mm




2006

W = 0.228 Kg/M
P = 148.82 mm




20110

W = 0.445 Kg/M
P = 135.93 mm




2005

W = 0.359 Kg/M
P = 190.44 mm



2009

W = 0.349 Kg/M
P = 157.62 mm



20111

W = 1.107 Kg/M
P = 275.01 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

TRANSPORT




2201

W = 0.433 Kg/M
P = 101.29 mm




2203

W = 0.615 Kg/M
P = 107.41 mm




2204

W = 0.791 Kg/M
P = 168.46 mm




2206

W = 0.286 Kg/M
P = 62.21 mm



2208


W = 0.226 Kg/M
P = 65.62 mm



2209


W = 0.290 Kg/M
P = 59.57 mm

TRANSPORT




2301

W = 0.521 Kg/M
P = 151.81 mm




2304

W = 0.380 Kg/M
P = 139.16 mm



2316

W = 0.196 Kg/M
P = 129.69 mm




2318

W = 1.455 Kg/M
P = 111.92 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

TRANSPORT




2327

W = 0.375 Kg/M
P = 170.40 mm




2328

W = 0.768 Kg/M
P = 335.72 mm



2329


W = 1.080 Kg/M
P = 469.76 mm



2330


W = 0.226 Kg/M
P = 161.40 mm

TRANSPORT




2331

W = 0.800 Kg/M
P = 197.63 mm




23311

W = 1.005 Kg/M
P = 371.55 mm




23312

W = 0.667 Kg/M
P = 123.68 mm



23313

W = 1.245 Kg/M
P = 248.74 mm




23330

W = 0.233 Kg/M
P = 90.27 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

TRANSPORT




2510

W = 0.235 Kg/M
P = 99.13 mm




2512

W = 0.215 Kg/M
P = 100.380 mm




2513

W = 0.337 Kg/M
P = 131.95 mm




2514

W = 0.359 Kg/M
P = 108.85 mm



2515


W = 0.248 Kg/M
P = 106.25 mm



2516

W = 0.333 Kg/M
P = 98.310 mm


TRANSPORT



26132

W = 1.733 Kg/M


P = 707.66 mm



2612

W = 0.902 Kg/M

P = 475.78 mm




2613

W = 1.536 Kg/M

P = 698.50 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


TRANSPORT



26824

W = 1.058 Kg/M


P = 610.94 mm



26431

W = 1.454 Kg/M

P = 437.18 mm




26262

W = 1.249 Kg/M


P = 599.51 mm

TRANSPORT




26386

W = 0.710 Kg/M
P = 169.51 mm




26821

W = 0.634 Kg/M
P = 261.52 mm



26432

W = 0.554 Kg/M
P = 211.43 mm




26823

W = 0.462 Kg/M
P = 192.65 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

TRANSPORT




26456

W = 1.110 Kg/M
P = 234.26 mm



26485


W = 1.578 Kg/M
P = 287.03 mm



26827

W = 1.171 Kg/M
P = 392.43 mm


TRANSPORT



2682

W = 1.459 Kg/M

P = 526.59 mm




2643

W = 1.201 Kg/M

P = 519.60 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


TRANSPORT



26822

W = 0.898 Kg/M


P = 373.48 mm



2618

W = 1.142 Kg/M

P = 460.60 mm




26580

W = 0.520 Kg/M

P = 220.04 mm


TRANSPORT



26842

W = 0.804 Kg/M


P = 322.64 mm



26844

W = 0.942 Kg/M

P = 379.28 mm




2609

W = 1.940 Kg/M

P = 474.21 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


TRANSPORT



26880

W = 2.032 Kg/M

P = 583.71 mm




26890

W = 2.606 Kg/M

P = 628.20 mm


TRANSPORT



2703

W = 0.979 Kg/M


P = 288.59 mm



2704

W = 2.218 Kg/M

P = 322.23 mm




2708

W = 0.876 Kg/M

P = 281.61 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


TRANSPORT



2705

W = 1.337 Kg/M

P = 597.20 mm




2707

W = 2.032 Kg/M

P = 636.16 mm


TRANSPORT



2701

W = 0.961 Kg/M


P = 530.46 mm



2709

W = 1.321 kg/m

P = 571.70 mm




27091

W = 0.434 kg/m

P = 209.761 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


TRANSPORT



2711

W = 0.468 Kg/M


P = 230.760 mm



2713

W = 1.064 Kg/M

P = 284.34 mm




27111

W = 0.894 Kg/M

P = 370.76 mm


TRANSPORT



27112

W = 0.792 Kg/M


P = 383.44 mm



27113

W = 0.905 Kg/M

P = 432.49 mm




27118

W = 0.544 Kg/M

P = 377.37 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


TRANSPORT



27021

W = 0.913 Kg/M

P = 228.25 mm




27119

W = 1.667 Kg/M


P = 397.45 mm

LADDER SECTION




30051

W = 0.419 Kg/M
P = 202.62 mm




30054

W = 0.331 kg/m
P = 200.83 mm



3033


W = 0.498 Kg/M
P = 201.83 mm



3007


W = 0.570 kg/m
P = 256.79 mm

LADDER SECTION




30073

W = 0.509 kg/m
P = 255.12 mm




3031

W = 0.312 Kg/M
P = 108.16 mm



30372


W = 0.319 Kg/M
P = 108.39 mm



30031


W = 0.273 Kg/M
P = 108.39 mm

LADDER SECTION




30044

W = 0.226 kg/m
P = 97.83 mm




30301

W = 0.256 Kg/M
P = 97.90 mm




30345

W = 0.200 Kg/M
P = 102.99 mm



3036

W = 0.262 Kg/M
P = 94.35 mm




9055

W = 0.336 Kg/M
P = 121.12 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

LADDER SECTION




3035

W = 0.238 kg/m
P = 176.41 mm




30371

W = 0.328 Kg/M
P = 182.58 mm




3008

W = 0.769 Kg/M
P = 315.20 mm



3037


W = 0.654 Kg/M
P = 301.89 mm



3023

W = 0.847 Kg/M
P = 429.70 mm


LADDER SECTION



30373

W = 0.641 Kg/M


P = 256.51 mm



30374

W = 0.650 Kg/M

P = 257.18 mm




30376

W = 0.571 Kg/M

P = 206.37 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


LADDER SECTION



3024

W = 0.304 Kg/M


P = 145.12 mm



30375

W = 0.287 Kg/M


P = 104.85 mm



3029

W = 0.338 Kg/M


P = 108.280 mm



30377

W = 0.595 Kg/M

P = 214.10 mm




9056

W = 0.555 Kg/M


P = 189.71 mm

HEAT SINK




4102

W = 1.110 kg/m
P = 644.55 mm




4104

W = 7.888 kg/m
P = 1413.01 mm



4106


W = 0.752 kg/m
P = 282.27 mm



4107


W = 0.460 kg/m
P = 377.54 mm

HEAT SINK




41081

W = 1.035 kg/m
P = 686.91 mm




4109

W = 0.594 Kg/M
P = 435.38 mm




4113

W = 0.309 kg/m
P = 143.40 mm



4114


W = 2.484 kg/m
P = 704.65 mm



4115


W = 0.281 kg/m
P = 167.88 mm

HEAT SINK




4116

W = 1.637 kg/m
P = 813.12 mm




4117

W = 3.878 kg/m
P = 923.21 mm



4118

W = 1.928 Kg/M
P = 499.70 mm




4120

W = 2.624 Kg/M
P = 1293.84 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

HEAT SINK




4121

W = 0.827 kg/m
P = 445.30 mm




41201

W = 22.230 Kg/M
P = 2772.78 mm



4122


W = 1.815 Kg/M
P = 905.58 mm



4123


W = 4.204 Kg/M
P = 570.33 mm

CLAMB CABLE




4052

W = 1.111 Kg/M
P = 139.35 mm




4051

W = 0.153 Kg/M
P = 62.98 mm




4057A

W = 0.321 Kg/M
P = 80.14 mm




4057B

W = 0.088 Kg/M
P = 45.14 mm



4061

W = 0.856 Kg/M
P = 140.36 mm




4063

W = 0.633 Kg/M
P = 123.24 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

PRINTING




4041

W = 0.323 Kg/M
P = 85.80 mm



4042


W = 0.412 Kg/M
P = 130.98 mm




4043

W = 0.758 Kg/M
P = 204.08 mm

ROLLING DOORS




NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
5082	56.50	10.00	0.70	0.171	153.40
5084	56.50	10.00	0.80	0.188	152.20
5083	64.17	9.60	0.70	0.178	166.42
50851	64.19	10.13	0.80	0.209	166.43
5085A	64.26	9.70	0.80	0.199	166.26
5085B	64.26	9.75	0.85	0.209	166.28
5085	64.42	9.90	1.00	0.240	166.37
5773	64.49	10.00	1.10	0.260	166.15
5767	65.48	10.00	0.70	0.180	167.68



NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
5768	55.00	8.70	0.70	0.164	142.60
5088	55.00	9.10	0.70	0.168	144.87
5769	55.00	10.5	1.00	0.235	153.07
5763	55.00	10.5	1.00	0.234	153.97
5766	55.48	9.30	0.70	0.172	148.20
5087	55.57	9.70	0.80	0.191	147.89
5081	56.50	10.00	0.70	0.181	151.53
5086	56.50	10.10	0.80	0.199	151.26
5081 B	56.50	10.00	1.00	0.223	150.04
5764	58.00	11.85	1.00	0.301	162.40


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROLLING DOORS




5094

W = 0.452 kg/m
P = 252.16 mm




5093

W = 0.458 kg/m
P = 242.90 mm



5791


W = 0.477 kg/m
P = 249.94 mm




5792

W = 0.421 kg/m
P = 234.96 mm

ROLLING DOORS




NO SECTION	A mm	B mm	T mm	W Kg/M	P mm
5733	41.65	23.80	0.80	0.262	215.16
5732	41.65	23.80	0.90	0.287	214.72
5092	42.00	24.00	1.00	0.316	215.57
5095	42.00	28.10	1.00	0.330	223.35
5098	42.00	24.00	1.15	0.354	214.87



5731

W = 0.356 kg/m
P = 240.88 mm




5090


W = 0.289 Kg/M
P = 238.49 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

ROLLING DOORS




NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
5091	100.00	25.00	1.00	0.793	455.36
5096	114.00	29.00	1.15	0.981	515.05
5097	100.00	25.00	1.15	0.875	453.67
5742	114.00	28.00	1.00	0.873	511.95



5741


W = 0.685 Kg/M
P = 441.58 mm



5743

W = 0.676 Kg/M
P = 435.49 mm


ROLLING DOORS



5752

W = 0.359 Kg/M


P = 295.97 mm



5753

W = 0.356 kg/M


P = 293.36 mm



5761

W = 0.242 Kg/M

P = 258.29 mm




5765

W = 0.365 Kg/M

P = 270.43 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


EXPANDA



5901

W = 0.302 Kg/M


P = 150.47 mm



5907

W =0.457 KG/M


P =240.35 mm



59051

W= 0.310 Kg/M

P= 221.57 mm




5905


W= 3.324 KG/M

P= 535.48 mm


HANDLES



5155
W = 0.376 Kg/M
P = 171.21 mm




5157
W = 0.816 kg/m
P = 292.04 mm




5158
W = 1.582 Kg/M
P = 358.94 mm


ACCESSORIES DOORS




5047
W = 1.652 Kg/M
P = 434.22 mm



51701
W = 0.584 Kg/M
P = 155.21 mm




51702
W = 0.287 Kg/M
P = 157.85 mm




51703
W = 0.711 kg/m
P = 218.82 mm


SWING DOORS



NO SECTION	A mm	T mm	W Kg/M	OP mm
5851	62.00	1.10	0.664	294.42
5050	63.35	1.15	0.699	299.33
5051	63.35	1.30	0.782	297.96
5051A	63.35	1.35	0.808	297.42




NO SECTION	A mm	T mm	W Kg/M	OP mm
5852	103.85	1.10	0.913	399.62
5854	114.10	1.10	0.974	419.89
5052	100.00	1.30	1.040	390.06



5053

W = 0.166 Kg/M

P = 112.63 mm




5853

W = 0.155 Kg/M

P = 116.20 mm


SWING DOORS




50161

W = 0.931 Kg/M


P = 371.31 mm



No.Sect	T mm	W Kg/M	P mm
50563	0.90	0.655	367.55
5056	1.05	0.787	364.25
5058	1.10	0.821	365.23




No.Sect	T mm	W Kg/M	P mm
58033	0.90	0.669	360.26
5801	1.05	0.777	357.53
5803	1.10	0.813	361.18
5060	1.10	0.810	360.37
5060A	1.35	0.960	352.53




No.Sect	T mm	W Kg/M	P mm
50573	0.90	0.693	372.52
5057	1.05	0.799	374.76
5059	1.10	0.839	327.45
5802	1.10	0.846	373.63
5059A	1.35	1.005	366.66


CASEMENT WINDOWS



NO SECT	A mm	B mm	T mm	W Kg/M	OP mm
72061	33.84	17.74	0.90	0.170	137.88
53763	33.85	17.80	0.80	0.151	137.44
5376	33.85	17.80	0.90	0.168	137.12
5062	33.85	17.80	1.00	0.189	138.13
50681	33.85	18.00	1.25	0.234	138.06
5064	33.85	18.00	1.00	0.192	140.09
72063	34.00	17.61	0.80	0.154	137.72




NO SECT	A mm	B mm	T mm	W Kg/M	OP mm
53753	41.00	30.40	0.80	0.252	220.54
5375	41.00	30.40	0.90	0.280	218.58
5063	41.00	30.40	1.00	0.305	217.10
5069	41.00	30.40	1.25	0.366	213.00



NO SECT	A mm	B mm	T mm	W Kg/M	P mm
53743	35.00	39.80	0.80	0.336	206.78
5374	35.00	39.80	0.90	0.373	205.10
5061	35.00	39.80	1.00	0.407	203.23
5067	35.00	39.80	1.25	0.489	198.40

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


CASEMENT WINDOWS



5373

W = 0.089 kg/m


P = 78.47 mm



5380

W = 0.189 kg/m


P = 140.91 mm



5398

W = 0.645 kg/m

P = 241.99 mm




53981

W = 0.700 kg/m

P = 272.96 mm


CASEMENT WINDOWS




5065

W = 0.512 Kg/M


P = 225.00 mm



No.Sect	T mm	W Kg/M	P mm
50661	0.80	0.400	240.23
5066	1.00	0.493	236.74




No.Sect	T mm	W Kg/M	P mm
5314	1.10	0.166	112.7
53141	0.90	0.139	115.29



No.Sect	A mm	T mm	W Kg/M	P mm
5315	50.80	1.10	0.213	144.30
53152	50.00	1.00	0.193	144.36

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


CASEMENT WINDOWS



5316

W = 0.216 Kg/M


P = 147.18 mm



5370

W = 0.389 Kg/M


P = 232.86 mm



5392

W = 0.935 kg/m

P = 190.64 mm




5399


W = 0.151 kg/m

P = 106.235 mm


SLIDING DOORS




No.Sect	T mm	W Kg/M	P mm
50021	0.90	0.488	395.08
5002	1.00	0.534	393.33
50022	1.20	0.638	390.85



No Sect	A mm	B mm	T mm	W Kg/M	OP mm
50036	50.00	28.00	0.70	0.333	228.75
50035	50.00	28.00	0.80	0.388	226.03
5010	50.05	28.00	0.85	0.409	225.71
50031	50.80	28.30	0.90	0.437	229.14
5003	50.80	28.30	1.00	0.483	228.34




No.Sect	T mm	W Kg/M	P mm
50052	0.80	0.388	257.00
50051	0.90	0.433	255.40
5005	1.00	0.478	253.80




No.Sect	T mm	W Kg/M	P mm
50062	0.80	0.309	276.29
50061	0.90	0.340	273.35
5006	1.00	0.369	270.13


SLIDING DOORS




No.Sect	T mm	W Kg/M	P mm
50072	0.80	0.310	287.03
50071	0.90	0.347	285.80
5007	1.00	0.384	285.41



No.Sect	T mm	W Kg/M	P mm
50082	0.80	0.485	430.46
50081	0.90	0.537	429.26
5008	1.00	0.587	427.25



No.Sect	T mm	W Kg/M	P mm
50092	0.80	0.399	321.34
50091	0.90	0.432	320.14
5012	1.00	0.461	316.08




5019


W = 0.500 Kg/M

P = 400.30 mm


SLIDING DOORS




50132
W = 0.214 kg/m
P = 194.05 mm




50142
W = 0.227 Kg/M
P = 157.89 mm



50152
W = 0.270 kg/m
P = 238.00 mm




5020
W = 0.383 Kg/M
P = 167.60 mm




5021
W = 0.189 Kg/M
P = 101.12 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

DOUBLE SPANDREL




51712
W = 0.456 kg/m
P = 204.33 mm




51714
W = 0.348 kg/m
P = 194.31 mm

DOOR JAMB 3 INCHI




50711

W = 0.425 kg/m
P = 367.36 mm



50712

W = 0.517 kg/m
P = 364.05 mm




50713

W = 0.472 kg/m
P = 365.82 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

DOOR JAMB 4 INCHI




5073

W = 0.649 kg/m
P = 456.10 mm



50731


W = 0.614 kg/m
P = 456.19 mm



5074

W = 0.885 kg/m
P = 481.83 mm


CURTAIN WALLS



5301

W = 0.414 Kg/M


P = 184.47 mm



5302

W = 0.167 Kg/M


P = 123.32 mm



5303

W = 0.529 Kg/M


P = 187.35 mm



5304

W = 0.277 Kg/M


P = 205.26 mm



5305

W = 0.576 Kg/M

P = 274.73 mm




5306

W = 0.471 Kg/M

P = 243.53 mm


CURTAIN WALLS



5307

W = 0.312 Kg/M


P = 225.53 mm



5308

W = 0.363 Kg/M


P = 141.27 mm



5309

W = 0.482 Kg/M


P = 201.05 mm



5310

W = 0.427 Kg/M


P = 210.22 mm



5311

W = 0.289 Kg/M

P = 201.60 mm




53651


W = 0.155 Kg/M

P = 113.29 mm


CURTAIN WALLS




5357
W = 0.633 Kg/M
P = 134.40 mm



5341
W = 0.526 kg/m
P = 298.80 mm




5342
W = 1.535 kg/m
P = 303.20 mm




5343
W = 2.054 kg/m
P = 370.47 mm


CURTAIN WALLS




5351
W = 0.278 Kg/M
P = 206.80 mm




5352
W = 0.689 Kg/M
P = 191.60 mm




5353
W = 0.143 Kg/M
P = 72.19 mm



5354
W = 0.611 Kg/M
P = 206.71 mm




5355
W = 0.739 Kg/M
P = 218.02 mm




5356
W = 0.800 Kg/M
P = 320.00 mm

CURTAIN WALLS




No Sect	A mm	B mm	T mm	W Kg/M	OP mm
53521	100.00	40.00	1.30	1.048	286.40
53522	100.00	40.00	2.00	1.511	286.00
5345	100.00	50.00	2.00	1.618	306.00



No Sect	A mm	B mm	T mm	W Kg/M	OP mm
53461	93.50	36.90	1.35	0.934	285.62
53462	92.60	35.60	2.00	1.346	270.80
53460	92.60	45.60	2.00	1.455	330.80

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


CURTAIN WALLS



53531

W = 0.292 Kg/M


P = 116.757 mm



5358

W = 0.355 Kg/M


P = 106.27 mm



53532

W = 0.255 Kg/M


P = 176.168 mm



5377

W = 0.109 Kg/M

P = 58.54 mm




53581


W = 0.692 Kg/M

P = 190.71 mm


CURTAIN WALLS



53441
W = 1.772 kg/m
P = 533.10 mm




7244
W = 0.255 kg/m
P = 116.03 mm




53536
W = 0.176 kg/m
P = 109.28 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


CURTAIN WALLS



53523
W = 2.044 kg/m
P = 382.64 mm




53533
W = 0.657 kg/m
P = 202.36 mm



53534
W = 0.288 kg/m
P = 157.60 mm


FOLDING DOORS



5701

W = 0.900 kg/m


P = 337.87 mm



57035

W = 0.872 kg/m

P = 369.62 mm




5704

W = 0.609 kg/m


P = 295.66 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

FOLDING DOORS




No.Sect	T mm	W Kg/M	P mm
57056	0.80	0.565	319.90
57055	1.00	0.694	318.13



57061


W = 0.947 kg/m

P = 341.469 mm



No.Sect	T mm	W Kg/M	P mm
57066	0.80	0.629	380.11
57065	1.00	0.773	376.76


CURTAIN TRACK



5401

W = 0.118 kg/m


P = 125.42 mm



5403

W = 0.183 kg/m


P = 148.33 mm



5404

W = 0.167 kg/m


P = 134.33 mm



5405

W = 0.158 kg/m


P = 135.51 mm



5451

W = 0.381 kg/m

P = 178.49 mm




5452


W = 0.451 kg/m

P = 201.29 mm

LIS PANCING




NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
5591	17.00	6.80	0.80	0.072	69.38
5592	21.50	7.30	0.80	0.083	79.38



5595

W = 0.124 kg/m


P = 77.84 mm



5596

W = 0.080 kg/m


P = 70.83 mm



5581

W = 0.037 kg/m

P = 39.84 mm




5597

W = 0.097 kg/m


P = 78.39 mm

LOUVRES




63501

W = 0.755 kg/m
P = 193.76 mm




63502

W = 0.752 kg/m
P = 214.00 mm



63500

W = 0.435 kg/m
P = 107.59 mm




63510

W = 0.761 kg/m
P = 122.96 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

LOUVRES




63530

W = 0.923 kg/m
P = 211.07 mm




6381

W = 0.407 kg/m
P = 269.46 mm



6302


W = 0.258 kg/m
P = 185.95 mm



6303


W = 0.459 kg/m
P = 332.20 mm

LOUVRES




6307

W = 0.617 Kg/M
P = 341.71 mm




63071

W = 0.445 Kg/M
P = 248.73 mm



6308


W = 0.461 kg/m
P = 279.27 mm



6352


W = 0.722 kg/m
P = 189.14 mm

LOUVRES




63521

W = 0.790 kg/m
P = 200.00 mm




63340

W = 2.478 Kg/M
P = 511.00 mm



63341


W = 0.453 Kg/M
P = 240.29 mm



63342

W = 0.580 Kg/M
P = 286.87 mm


SHOW CASES



60011

W = 0.167 Kg/M


P = 84.70 mm



60021

W = 0.211 Kg/M


P = 106.70 mm



6082

W = 0.284 Kg/M

P = 299.87 mm




6083

W = 0.296 Kg/M


P = 312.85 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


SHOW CASES



NO SECTION	A mm	T mm	R mm	W Kg/M	P mm
6015A	20.50	0.70	8.50	0.144	78.35
6015	20.50	0.80	8.50	0.163	77.71
60081	23.00	0.70	8.50	0.162	87.71
6016A	23.50	0.70	8.50	0.166	89.71
6016	23.50	0.80	8.50	0.189	89.71
6010	24.00	0.80	8.50	0.194	92.09
6009	25.00	0.90	8.50	0.227	96.35
6007	25.00	1.00	8.50	0.251	96.35
6013	35.00	2.00	10.00	0.694	135.45




NO SECTION	A mm	B mm	T mm	R mm	W Kg/M	P mm
6017A	34.50	23.00	0.70	8.50	0.206	110.71
6017	34.50	23.00	0.80	8.50	0.234	110.71
6008	38.10	25.40	0.90	8.50	0.293	123.35
6005	38.10	25.40	1.00	8.50	0.324	123.35
6006	35.00	23.00	0.70	8.50	0.208	112.35
60056	40.00	25.00	1.20	7.00	0.398	127.00
6014	50.00	35.00	1.50	10.00	0.650	165.45




NO SECTION	A mm	B mm	T mm	R mm	W Kg/M	P mm
6012	23.00	34.50	0.85	8.50	0.288	144.49
6039	24.00	35.00	0.80	9.00	0.280	150.25
6030	24.70	34.80	0.80	8.50	0.283	151.07
6032	25.00	34.80	0.90	8.50	0.314	148.89
6023	25.40	38.10	1.10	8.50	0.406	157.41


SHOW CASES



NO SECTION	A mm	B mm	T mm	R mm	W Kg/M	P mm
6011	23.00	34.50	0.85	2.50	0.296	147.45
6038	24.00	35.00	0.80	2.00	0.287	153.25
6029	24.70	34.80	0.80	3.00	0.288	153.43
6029A	24.70	34.80	0.85	3.00	0.305	153.23
6031	25.00	34.80	0.90	2.50	0.323	151.85
6024	25.00	38.00	1.10	3.00	0.412	159.57




NO SECTION	A mm	T mm	R mm	W Kg/M	P mm
6046	23.00	0.70	8.50	0.196	121.14
6026A	23.00	0.70	8.50	0.197	122.14
6026	23.50	0.80	8.50	0.227	123.74
6025	25.00	0.80	8.50	0.240	129.74
6028A	25.00	0.85	8.50	0.253	129.49
6037	30.00	0.70	9.00	0.250	152.74
6034	30.00	0.80	8.50	0.284	151.67




NO SECTION	A mm	T mm	R mm	W Kg/M	P mm
6047	23.00	0.70	2.50	0.202	124.93
6027	23.50	0.80	2.50	0.232	126.27
6028	25.00	0.80	2.50	0.245	132.27
6042	30.00	0.70	2.50	0.255	152.93
6035	30.00	0.80	3.00	0.289	154.03
6036	30.00	0.80	2.00	0.291	155.25

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

SHOW CASES




NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
60731	120.00	20.00	0.80	0.439	405.27
6073B	120.00	25.00	0.80	0.461	439.91
6073A	120.00	25.00	0.85	0.490	428.19
6073	120.00	25.00	0.90	0.518	425.76
60772	134.00	24.00	0.80	0.465	432.00
6077A	134.00	24.00	0.80	0.487	450.51
6077	134.00	24.00	0.90	0.547	449.76
6075	134.00	24.00	1.00	0.606	449.03




NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
60741	120.00	20.00	0.80	0.456	420.71
6074B	120.00	25.00	0.80	0.478	440.92
6074A	120.00	25.00	0.85	0.510	445.40
6074	120.00	25.00	0.90	0.537	441.55
60781	134.00	24.00	0.80	0.490	454.72
6078A	134.00	24.00	0.80	0.506	464.13
6078	134.00	24.00	0.90	0.566	465.55
6076	134.00	24.00	1.00	0.628	464.82


SHOW CASES



NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
6063	9.50	21.00	0.80	0.124	103.82
60632	9.50	20.00	0.80	0.120	100.16




NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
6124	8.00	35.00	0.80	0.165	153.71
6122	9.00	36.00	0.80	0.171	159.03
6062	9.00	36.00	1.00	0.220	158.71
60681	9.00	39.00	0.80	0.185	171.71
6068	9.00	40.00	1.00	0.235	174.28



NO SECTION	A mm	B mm	T mm	W Kg/M	OP mm
6064	21.00	11.00	0.80	0.119	110.34
6069	23.00	11.00	0.70	0.106	112.80
6051A	23.00	12.00	0.80	0.129	120.40
6066	23.50	9.50	0.80	0.115	107.80
6067	24.00	11.00	0.90	0.143	119.20

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


BOTTOM RAIL



6120

W = 0.103 kg/m


P = 58.18 mm



6115

W = 0.150 kg/m


P = 54.78 mm



6065

W = 0.109 kg/m

P = 56.87 mm




6070

W = 0.121 kg/m

P = 56.59 mm


SPANDRELS



6201

W = 0.254 Kg/M


P = 235.31 mm



6202

W = 0.360 Kg/M

P = 268.68 mm




6204

W = 0.260 Kg/M

P = 240.71 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


SPANDRELS



6205

W = 0.406 Kg/M


P = 370.63 mm



6206

W = 0.201 Kg/M

P = 212.60 mm




6207

W = 0.200 Kg/M

P = 211.80 mm


SPANDRELS



6208

W = 0.281 Kg/M


P = 260.86 mm



6209

W = 0.284 Kg/M

P = 234.24 mm




6210

W = 0.359 Kg/M

P = 266.929 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


SPANDRELS



6221

W = 0.223 Kg/M


P = 236.49 mm



6212

W = 0.368 Kg/M

P = 321.41 mm




9003

W = 0.240 Kg/M


P = 215.67 mm

SHOP FRONT 3 INCHI




7141

W = 0.417 kg/m
P = 366.57 mm



7143

W = 0.456 kg/m
P = 419.187 mm




7145

W = 0.384 kg/m
P = 353.02 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

SHOP FRONT 3 INCHI




7142

W = 0.472 kg/m
P = 399.27 mm



7144


W = 0.512 kg/m
P = 452.15 mm




7149

W = 0.439 Kg/M
P = 385.39 mm


SHOP FRONT 3 INCHI



7161
W = 0.410 Kg/M
P = 362.39 mm




7163
W = 0.448 Kg/M
P = 413.78 mm




7165
W = 0.377 Kg/M
P = 348.49 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


SHOP FRONT 3 INCHI




7166
W = 0.160 Kg/M
P = 145.18 mm




7146
W = 0.162 Kg/M
P = 146.29 mm




7167
W = 0.156 Kg/M
P = 133.56 mm



7147
W = 0.154 Kg/M
P = 133.41 mm




7168
W = 0.228 Kg/M
P = 198.93 mm




7148
W = 0.226 Kg/M
P = 198.77 mm


SHOP FRONT 4 INCHI



NO SECTION	T mm	W Kg/M	P mm
75013	0.90	0.598	462.91
7501	1.00	0.663	462.82




NO SECTION	T mm	W Kg/M	P mm
75033	0.90	0.634	518.25
7503	1.00	0.708	519.17




NO SECTION	T mm	W Kg/M	P mm
75053	0.90	0.542	445.11
7505	1.00	0.607	445.05

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


SHOP FRONT 4 INCHI



NO SECTION	T mm	W Kg/M	P mm
75023	0.90	0.646	494.04
7502	1.00	0.717	494.27




NO SECTION	T mm	W Kg/M	P mm
75043	0.90	0.681	550.42
7504	1.00	0.762	550.62



NO SECTION	T mm	W Kg/M	P mm
75153	0.90	0.592	476.89
7515	1.00	0.661	476.50


SHOP FRONT 4 INCHI




7506 A

W = 0.244 kg/m


P = 200.24 mm



NO SECTION	T mm	W Kg/M	P mm
75073	0.90	0.224	173.77
7507	1.00	0.244	173.48



NO SECTION	T mm	W Kg/M	P mm
75083	0.90	0.315	247.89
7508	1.00	0.345	246.19




7154

W = 0.181 kg/m

P = 134.79 mm


SHOP FRONT 3&4 INCHI



71521

W = 0.080 kg/m


P = 62.34 mm



71503

W = 0.149 kg/m


P = 111.31 mm



75501

W = 0.136 kg/m


P = 102.96 mm



71501

W = 0.152 kg/m


P = 112.60 mm



71502

W = 0.136 kg/m

P = 102.93 mm




7153

W = 0.087 kg/m

P = 65.45 mm


WINDOW WALL




72051

W = 0.569 kg/m

P = 358.43 mm



NO SECTION	A mm	B mm	C mm	T mm	W Kg/M	OP mm
72012	70.00	48.00	30.00	1.00	0.551	387.21
72015	70.00	48.00	30.00	1.05	0.569	385.69
72091	70.00	48.00	30.00	1.15	0.620	384.51




72072

W = 0.320 kg/m

P = 198.51 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


WINDOW WALL



72013

W = 0.570 kg/m


P = 433.04 mm



72104

W = 0.932 kg/m

P = 298.56 mm




72105

W = 0.821 kg/m

P = 323.01 mm


WINDOW WALL



7355

W = 0.563 kg/m


P = 404.76 mm



72075

W = 0.365 kg/m

P = 210.73 mm




7210

W = 0.712 kg/m

P = 316.106 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


WINDOW WALL



7208

W = 0.511 kg/m


P = 375.513 mm



72071

W = 0.251 kg/m


P = 179.959 mm



53191

W = 0.287 kg/m

P = 200.11 mm




72072

W = 0.320 kg/m

P = 198.51 mm


WINDOW WALL



72073

W = 0.209 kg/m

P = 182.96 mm




53912

W = 1.387 kg/m

P = 391.55 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


WINDOW WALL



53911

W = 0.890 kg/m

P = 459.21 mm




53913

W = 0.492 kg/m


P = 259.12 mm

FURNITURE




80361

W = 1.819 Kg/M
P = 300.00 mm




80472

W = 1.233 Kg/M
P = 132.16 mm



8044

W = 0.216 Kg/M
P = 73.65 mm




80488

W = 0.808 Kg/m
P = 92.28 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

FURNITURE




8057

W = 0.345 Kg/M
P = 59.85 mm




80599

W = 1.176 Kg/M
P = 160.50 mm



80586


W = 5.951 Kg/M
P = 563.02 mm



8060


W = 2.119 Kg/M
P = 237.42 mm

FURNITURE




80596

W = 0.698 Kg/M
P = 95.28 mm




80603

W = 0.768 Kg/M
P = 138.80 mm



8201

W = 0.399 Kg/M
P = 117.31 mm




80620

W = 1.582 Kg/M
P = 259.04 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

FURNITURE




8054

W = 0.716 Kg/M
P = 223.25 mm




80541

W = 0.300 Kg/M
P = 124.53 mm



80632


W = 1.453 Kg/M
P = 223.38 mm




80631

W = 1.689 Kg/M
P = 340.88 mm


FURNITURE




8040
W = 0.533 Kg/M
P = 149.440 mm




8041
W = 0.350 Kg/M
P = 146.00 mm




80401
W = 0.429 Kg/M
P = 150.740 mm




80411
W = 0.680 Kg/M
P = 158.683 mm



80415
W = 0.746 Kg/M
P = 182.008 mm




80543
W = 0.567 Kg/M
P = 186.41 mm




80402
W = 0.589 Kg/M
P = 257.48 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


FURNITURE




8300
W = 0.409 kg/m
P = 96.78 mm




9030
W = 0.635 kg/m
P = 117.14 mm



9031
W = 0.434 kg/m
P = 90.00 mm




9032
W = 0.374 kg/m
P = 78.54 mm




9037
W = 0.699 kg/m
P = 195.67 mm

TENTS




90621

W = 10.284 kg/m
P = 733.03 mm



90622

W = 6.743 kg/m
P = 704.18 mm




90623

W = 3.137 kg/m
P = 404.27 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

DIFFUSER




9352

W = 0.150 kg/m
P = 111.77 mm




9353

W = 0.257 kg/m
P = 177.50 mm



9354


W = 0.329 kg/m
P = 227.71 mm



9355

W = 0.194 kg/m
P = 135.94 mm


DIFFUSER



93561

W = 0.243 Kg/M


P = 173.64 mm



93554

W = 0.171 Kg/M


P = 125.12 mm



93555

W = 0.307 Kg/M

P = 224.11 mm




93553

W = 0.085 Kg/M

P = 43.18 mm

PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division


DIFFUSER



93556

W = 0.228 Kg/M


P = 167.12 mm



93557

W = 0.195 Kg/M


P = 146.87 mm



9356

W = 0.098 Kg/M


P = 40.44 mm



93561

W = 0.243 Kg/M

P = 173.64 mm




93562

W = 0.337 Kg/M

P = 213.65 mm


DIFFUSER



93563

W = 0.152 Kg/M


P = 116.39 mm



93564

W = 0.145 Kg/M


P = 106.75 mm



93565

W = 0.144 Kg/M


P = 108.00 mm



93566

W = 0.095 Kg/M

P = 61.94 mm




93574

W = 0.093 Kg/M

P = 69.10 mm


DIFFUSER



93567

W = 0.091 Kg/M


P = 63.69 mm



93575

W = 0.223 Kg/M


P = 148.79 mm



93576

W = 0.151 Kg/M

P = 115.57 mm




9082

W = 0.170 kg/m


P = 110.57 mm

EXHIBITION




90241

W = 1.158 Kg/M
P = 279.01 mm



90245

W = 2.058 Kg/M
P = 424.75 mm




90252

W = 1.005 Kg/M
P = 355.00 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

EXHIBITION




9027

W = 0.642 Kg/M
P = 232.07 mm




9028

W = 0.784 Kg/M
P = 242.28 mm



9042


W = 0.988 Kg/M
P = 292.48 mm



9043


W = 0.822 Kg/M
P = 261.59 mm

CONVEYOR



91042

W = 15.596 kg/m
P = 814.97 mm




91043

W = 7.843 kg/m
P = 341.55 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

CONVEYOR




92003

W = 1.998 kg/m
P = 327.68 mm



92004


W = 4.379 kg/m
P = 897.00 mm



92005


W = 3.894 kg/m
P = 538.11 mm

PARTITION




9007

W = 0.133 Kg/M
P = 111.00 mm




9301

W = 0.08 Kg/M
P = 86.06 mm



9302

W = 0.381 Kg/M
P = 333.49 mm




9303

W = 0.229 Kg/M
P = 212.40 mm


PT. HANJAYA PERKASA METALS INDONESIA
Aluminium Extrusion & Fabrication Division

PARTITION




9304

W = 0.506 Kg/M
P = 377.30 mm




9305

W = 0.187 Kg/M
P = 160.46 mm



93071


W = 0.195 Kg/M
P = 207.08 mm



93073


W = 0.223 Kg/M
P = 236.878 mm

OTHER




90332

W = 0.322 Kg/M
P = 116.29 mm




90341

W = 0.392 Kg/M
P = 123.25 mm



9035


W = 0.717 Kg/M
P = 314.85 mm



9049


W = 0.268 kg/m
P = 144.07 mm

OTHER




92001

W = 0.673 kg/m
P = 170.34 mm




9026

W = 1.162 Kg/M
P = 211.32 mm



9125

W = 0.231 Kg/M
P = 142.38 mm



92002

W = 0.223 kg/m
P = 77.56 mm

Connect with us.

Email

anugrahterangsj@yahoo.com

Website

anugrahterangsejahtera.com

Call us

+62 813 5755 0433

